

TECHNICAL DATA SHEET

VISCOATEX™ 560

Acrylic thickener for water-based systems

ASE Acrylic Thickener



24% Bio Carbon Content (only for EMEA supply)
-24% Carbon Footprint Reduction (only for EMEA supply)

TYPICAL CHARACTERISTICS

Nature	Aqueous dispersion of an acrylic copolymer
Appearance	Low viscous white milky liquid
Solid Content (%)	28
Active Content (%)	28
pH	3.2
Specific gravity	1.06
Solvent	Water
Total Bio content (%)	24

DESCRIPTION

VISCOATEX™ 560 is a formaldehyde-free, APEO-free, Heavy metal-free and Solvent-free non associative thickener designed for use in adhesives, paints, sealants and mastics. VISCOATEX™ 560 imparts robustness versus variations of ingredients such as latex type, surfactant and co-solvent.

RECOMMENDED ADDITION LEVEL

0.1 - 1.5 % as supplied based on total formulation weight.

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 220L Drum
- Bulk

HANDLING & STORAGE

It can be irreversibly altered by frost. It should be protected from the effects of weathering, stored between 5 and 40°C and protected from direct sun exposure. Once opened, packaging should be resealed immediately after use. In these conditions, this product should be used within 6 months from delivery.

PROCESSING INSTRUCTIONS

Supplied as a low viscosity liquid emulsion, VISCOATEX™ 560 is very easy to handle. VISCOATEX™ 560 may be used either at the beginning of the formulation or in the pigment grinding or in the finished product to adjust the final viscosity. The pH of the formulated product must be controlled to obtain good performance and reproducible viscosity. Film-forming product, surface may dry in contact with air. If necessary, filter the product prior its use.

MARKETS

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

Adhesives & Sealants

- Assembly
- Other Adhesives
- Sealants

KEY BENEFITS

FORMULATION

- Cost in use
- Easy handling
- Color acceptance



STORAGE

- Syneresis resistance
- Antisettling
- In-can appearance
- Viscosity stability



APPLICATION

- Brushability
- Rollability
- Sag resistance



FILM PROPERTIES

- Gloss
- Rub out
- Stain resistance



SAFER SOLUTIONS

- APEO Free*
- Heavy Metal Free*
- LiCl Free*
- MIT Free*
- Solvent Free*

* Not intentionally added but not specifically measured (not part of product specification)

- Total Bio content (%) **24**

VISCOATEX™ 560

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

THICKENING MECHANISM

Non Associative
Self Association



VISCOSITY CONTRIBUTION

Low Shear contribution
Mid Shear contribution
High Shear contribution



PVC

PVC Low
PVC Mid
PVC High



Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80