



### **PRODUCT DETAILS**

**ENBUILD 373** is an aqueous styrene-butadiene copolymer dispersion for the modification of cementitious mixtures and other hydraulic setting systems

## **APPLICATIONS/ADVANTAGES**

- Bonding agent, cementitious waterproofing and repair mortar.
- Provides excellent water impermeability
- Offers good workability at reduced water/ cement ratio.
- Improved bonding and adhesion to substrates.
- Improved toughness and flexibility.
- Mixes can be applied in thinner sections.

#### SAFETY AND HANDLING

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles, gloves and face shield while handling the product

(For any detail information please refer MSDS)

### PRODUCT SPECIFICATIONS

Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic and nonionic
Total Solids (%)	37.0 <u>+</u> 1.0
pH at 25°C	9.0 <u>+</u> 1.0
Brookfield Viscosity LVF (CPS) SP.1, 12 RPM at 25°C	30 Max.
Surface Tension (Dynes/cm) at 25°C	40 <u>+</u> 5.0
Specific Gravity	1.030 <u>+</u> 0.010
Dilution with water	Dilutable in any proportion
Compatibility	Compatible with Cement and Concrete mixture

# STORAGE RECOMMENDATIONS

- Store between temperature 5°C 40°C
- Keep containers closed when not in use
- Shelf life: Six months from the date of manufacturing provided stored under shade away from sunlight and direct heat, well protected from freezing.
- Packing: 220/50 kg Drums / 1000kg IBC / Bulk Packing

TDS ENBUILD 373 JUBILANT INDUSTRIES

Disclaimer: These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Jubilant recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale