



Date of issue: 22/10/2021

EXODISP C 7905

EXODISP C 7905 is an APEO free waterborne dispersion of styrene-acrylic copolymer free of plasticizer and solvent.

It has good film forming and binding properties, with excellent resistance towards alkalis and water.

Dispersion Properties

| | |
|-------------------------------------------|-------------------|
| Polymer Type | Styrene - acrylic |
| Emulsifying System | Anionic |
| Brookfield Viscosity (RVT 4/20 rpm, 23°C) | 1000 - 2000 mPas |
| Total Solids Content | 55 % |
| pH | 7.0 – 9.0 |
| particle size | ca. 250 nm |

Film Properties

| | |
|------------|--------------------|
| Appearance | Clear, transparent |
| Surface | Slightly tacky |
| Tg (calc) | - 10 °C |

Applications

EXODISP C 7905 is used for the preparation of flexible mortars, waterproof 2-component cements and flexible cement-containing insulation coatings.

EXODISP C 7905 can also be used in the production of crack-filling systems and flexible coatings for flat roofs.

Storage

The shelf life is 6 months in the shade at a temperature from +5°C to 30 °C

note: All recommendations for use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge at the time such recommendations are made. As additional information is learned, these recommendations may be updated. They may also be impacted by circumstances outside our control. Notwithstanding any such recommendations, the user shall remain responsible for satisfying himself that the product as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The user shall ensure that the intended use of the products will not infringe any third party's intellectual property rights.